

TECHNICAL DATA SHEET

Transparent non sealable, modified – slip, high glossy, high energy treated, for high speed labeling application.

PRODUCT DESCRIPTION

Chiripal Poly Films CLA is transparent non heat salable corona treated both side, for over lamination in labeling application. One side is high glossy, high energy treated surface for printing, and other side is modified slip, treated. The high energy treated side for facilitating anchorage with various hot melt and pressure sensitive adhesives.

PRODUCT FEATURES


- Superb gloss and transparency
- Excellent printability and receptivity to laminating adhesive
- Excellent antistatic and modified
- Very good mold resistance
- Excellent machine performance
- Very good dimensional stability

APPLICATIONS

- Wrap around & pressure sensitive labels.
- Roll – Fed labels
- Printing & laminations
- Suitable for high speed label machine

*Available in inside / outside corona treated as per customer requirement

SHEET STRUCTURE



TECHNICAL INFORMATION

PROPERTIES	TEST METHOD	UNIT	CB15NB-CLA	CB18NB-CLA	CB20NB-CLA	CB25NB-CLA	CB30NB-CLA	CB35NB-CLA
Nominal Thickness (±3%)	ASTM D-374	Micron	15	18	20	25	30	35
		(Gauge)	60	72	80	100	120	140
Unit weight	Internal	gm/m ²	13.7	16.4	18.2	22.8	27.3	31.9
Yield	Internal	m ² /kg	73.3	61.1	54.9	44.0	36.6	31.4
Treatment Level	ASTM D-2578	dyne/cm	38 min					
Coefficient of Friction	ASTM D-1894	Kinetic	0.25-0.30					
Haze	ASTM D-1003	%	< 1.0					
Gloss at 45°	ASTM D-2457	-	95					
Tensile Strength at Break	ASTM D-882	kg/cm ²	MD	1350				
			TD	2900				
		(KPsi)	MD	19.2				
			TD	44.2				
Elongation at Break	ASTM D-882	%	MD	180				
			TD	80				
Thermal Shrinkage (at 120°C / 5 min)	Internal	%	MD	<5.0				
			TD	<3.0				

MD – Machine Direction, TD – Transverse Direction, NT – Non Treated

FOOD CONTACT

Chiripal Poly Films complies with EC and FDA regulations. Specific document and MSDS are available on request.

STORAGE & HANDLING

Chiripal Poly Films do not require special storage conditions. A storage temperature below 30°C & humidity 55±5 % is recommended in order to avoid any deterioration of the film surface properties. Excess humidity and heat can cause problem such as fast treatment decay, film becomes more hazy / slippery which can affect the quality of printing and coating. It is advisable to use the material on FIFO basis. The film should be conditioned in operating environment for 24 hours before any kind of processing. CP-Films is best suitable for use up to 3 months from date of production except for metallised side surface tension.

DISCLAIMER

The property given in the technical data sheet do not constitute product specification but represent typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Chiripal Poly Films Ltd. does not guarantee the typical values. Chiripal Poly Films Ltd. reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.