

TECHNICAL DATA SHEET

Transparent one side sealable with high seal strength, other side corona treated.

PRODUCT DESCRIPTION

Chiripal Poly Films SS is transparent co-extruded one side heat sealable with high seal strength and other side corona treated film. Corona treated surface is specifically designed to provide good adhesion of ink and lamination adhesive during conversion. The non treated heat-seal surface have high seal strength and sealing range which gives optimum performance on packaging machines.

PRODUCT FEATURES


- High heat seal strength and hot tack on sealable side
- Good printability and suitable for lamination with other substrates
- Good optical properties
- Good stiffness & mechanical Properties
- Good barrier properties

APPLICATIONS

- Single / two ply printing lamination
- Bread Packaging
- Flexible packaging
- General wrapping

* Available in inside / outside corona treated as per customer requirement

SHEET STRUCTURE



TECHNICAL INFORMATION

PROPERTIES	TEST METHOD	UNIT	CB20SI-SS	CB25SI-SS	CB30SI-SS	CB35SI-SS	CB40SI-SS	CB45SI-SS
Nominal Thickness (±3.0%)	ASTM D-374	Micron	20	25	30	35	40	45
		(Gauge)	80	100	120	140	160	180
Unit weight	Internal	gm/m ²	18.0	22.5	27.1	31.6	36.2	40.8
Yield	Internal	m ² /kg	55.5	44.4	36.9	31.6	27.6	24.5
Treatment Level	ASTM D-2578	dyne/cm	38 min					
Coefficient of Friction	ASTM D-1894	Kinetic (NT/NT)	0.35-0.40					
Haze	ASTM D-1003	%	2.5	2.5	2.8	2.8	2.8	2.8
Gloss at 45°	ASTM D-2457	-	90					
Tensile Strength at Break	ASTM D-882	kg/cm ²	MD	1300				
			TD	2900				
		(KPsi)	MD	19.2				
			TD	41.2				
Elongation at Break	ASTM D-882	%	MD	200				
			TD	90				
Thermal Shrinkage (at 120°C / 5 min)	Internal	%	MD	<5.0				
			TD	<3.0				
Heat Seal Range (NT side)	Internal	°C	115-140					
Sealing Strength (NT side) (120°C / 2 Bar/1 sec)	Internal	gm/25mm	>950					
WVTR (38°C & 90% RH)	ASTMF-1249	gm/m ² /day	6.5	6.0	5.7	5.4	5.0	5.0
		(gm/100in ² /day)	0.42	0.39	0.37	0.35	0.32	0.32
OTR (23°C & 0% RH)	ASTM D-3985	cc/m ² /day	1800	1600	1600	1400	1400	1400
		cc/100in ² /day)	116	103	103	90	90	90

MD – Machine Direction, TD – Transverse Direction, NT– Non Treated

FOOD CONTACT

Chiripal Poly Films complies with EC and FDA regulations. Specific document and MSDS are available on request.

STORAGE & HANDLING

Chiripal Poly Films do not require special storage conditions. A storage temperature below 30°C & humidity 55±5 % is recommended in order to avoid any deterioration of the film surface properties. Excess humidity and heat can cause problem such as fast treatment decay, film becomes more hazy / slippery which can affect the quality of printing and coating. It is advisable to use the material on FIFO basis. The film should be conditioned in operating environment for 24 hours before any kind of processing. CP-Films is best suitable for use up to 6 months from date of production.

DISCLAIMER

The property given in the technical data sheet do not constitute product specification but represent typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Chiripal Poly Films Ltd. does not guarantee the typical values. Chiripal Poly Films Ltd. reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.